

Technical Data Sheet – ASTM Standard

Lundhs Royal Blue

Lundhs Royal Blue has large crystals and bright blue colour. The material is exclusively produced by Lundhs.

Technical Properties	Standard	Mean Values
stone name:		Monzonite (Larvikite)
structure:		coarse grained
texture:		oriented feldspar crystals with lustre
Compressive Strength	ASTM C-170	26,340 PSI
Flexural Strength	ASTM C-880	1,901 PSI
Abrasion Resistance	ASTM C-1353	180.3 wear index value
Water Absorption	ASTM C-97	0.12 %
Density	ASTM C-97	169.3 lb/ft ²
Modulus of Rupture	ASTM C-99	2,525 PSI
petrographic composition:		feldspar 85% pyroxene 4% olivine 1% amphibole 3% nepheline 3% magnetite 3% apatite <1% biotite 1%

* PSI: Pounds Per Square Inch

** Method: American Society for Testing and Materials

Source: ABIC Testing Laboratories, Inc.